

Technisches Datenblatt



Produkt: 108

Hersteller: HENKEL KGAA

Warengruppe: KLEBSTOFF

Artikelgruppe: 1-K KLEBSTOFF

Download: 23.09.2021

LOCTITE ESP 108

Dieses Datenblatt wurde Ihnen von der Firma tewipack Uhl GmbH zur Verfügung gestellt. Die Firma tewipack Uhl GmbH übernimmt keinerlei Verantwortung für die Aktualität und die Richtigkeit der enthaltenen Informationen. Die Eigenschaften der Produkte können sich aufgrund verschiedener Einflüsse wie beispielsweise Zusammensetzung und Zustand des Substrats, Unreinheiten in oder auf dem Substrat, Temperatur und Luftfeuchtigkeit bei der Lagerung und Umgebungsbedingungen während der Anwendung ändern. Bei Verwendung dieses Produkts in Kombination mit anderem Material ist der Kunde dafür verantwortlich, durch eigene Tests zu prüfen, ob das Produkt für die geplante Kombination geeignet ist und ob diese Kombination die erwarteten Ergebnisse liefert



LOCTITE[®] ESP108

July 2007

Description:

Loctite ESP108 is a paste adhesive which flows like solder when cured. It is designed to provide maximum resistance to impact, shear, cleavage and tensile loads. The durability, chemical resistance and high temperature performance are extremely good. ESP108 will bond to a wide variety of surfaces, including oily steel, and performance is usually limited by the strength of the adherends themselves. In many applications it can replace traditional fixing techniques to give enhanced appearance and greater design flexibility.

Physical Properties

Colour	Silver
Viscosity (mPa.s)	170,000
Specific Gravity	1.5

Storage:

When stored in the original unopened containers at 5-7°C, the shelf life of this product is 12 months from the date of manufacture.

Typical Performance	
Shear Strength (MPa) - Steel*	30
Coeff. of Thermal Expansion (mm/mm/°C)	45×10^{-6}
Maximum Gap Fill (mm)	< 0.5

Service Temperature:

The recommended service temperature range for this product is -40 to +180°C. However higher temperatures may be endured for short periods providing the adhesive is not unduly stressed.

With joints involving materials such as ferrites or SMC bond strengths are generally greater than that of the substrate itself. The bond strengths measured on the be affected by the modulus of the metal and the thickness of the actual components.

Handling:

Full information can be obtained from the Material Safety Data Sheet (MSDS). Users are reminded that all materials, whether innocuous or not, should be handled according to the principles of good industrial hygiene more ductile metals, such as copper and its alloys, will

Cure Time at:-	100°C	120°C	150°C	180°C
Minutes* (in an air circulating oven)	240	60	45	20

*The actual cure time for any application is dependent on the time it takes for the adhesive to reach temperature. Larger components, or batch curing, will require a longer warm up time and the cure cycle may be extended. The use of alternative heating methods may also affect the time required to achieve full cure; Hotplates, Infra-Red lamps or Induction heating will generally give a faster cure.

Directions for Use:

Surfaces should be clean, dry and grease free before applying the adhesive. Where ultimate performance is required then the surfaces should be shot blasted, or lightly abraded, in the presence of **Loctite SIP**.

The adhesive should be extruded using a bead diameter that will allow complete coverage of the bond area. Care should be taken not to include, or trap, any air within the joint. Normally it should be applied to only one surface.

Assemble the parts and squeeze together with sufficient pressure to ensure the adhesive spreads to cover the entire Loctite ESP108 is approved to the Waters Byelaws Scheme as being suitable for contact with potable (drinking) bond area. Jig the components using a light clamping pressure and place in the oven to cure. Do not disturb the joint water until the adhesive has cured.

The information given and the recommendations made herein are based on our experience and are believed to be accurate. No guarantee as to, or responsibility for, their accuracy can be given or accepted, however, and no statement herein is to be treated as a representation or warranty. In every case we urge and recommend that purchasers, before using any product, make their own tests to determine, to their own satisfaction, its suitability for their particular purposes under their own operating conditions

17/07/07