

Technisches Datenblatt



Produkt: 3820

Hersteller: HENKEL KGAA

Warengruppe: 3DP

Artikelgruppe: 3DP RESINS

Download: 07.08.2020

LOCTITE® 3D 3820

Dieses Datenblatt wurde Ihnen von der Firma tewipack Uhl GmbH zur Verfügung gestellt. Die Firma tewipack Uhl GmbH übernimmt keinerlei Verantwortung für die Aktualität und die Richtigkeit der enthaltenen Informationen. Die Eigenschaften der Produkte können sich aufgrund verschiedener Einflüsse wie beispielsweise Zusammensetzung und Zustand des Substrats, Unreinheiten in oder auf dem Substrat, Temperatur und Luftfeuchtigkeit bei der Lagerung und Umgebungsbedingungen während der Anwendung ändern. Bei Verwendung dieses Produkts in Kombination mit anderem Material ist der Kunde dafür verantwortlich, durch eigene Tests zu prüfen, ob das Produkt für die geplante Kombination geeignet ist und ob diese Kombination die erwarteten Ergebnisse liefert

Confidential

July 2018

PRODUCT DESCRIPTION

Loctite® 3D 3820 is a clear light curing acrylic resin that may be used for prototyping via stereo-lithography. Loctite® 3D 3820 cures with very short exposure to monochromatic light sources such as LED or Laser. Printed articles made from Loctite® 3D 3820 exhibit good print resolution and high optical clarity. Loctite® 3D 3820 is a low viscosity liquid that is printable at room temperature across various Laser SLA and DLP Platforms.

Technology	Stereolithography Resin
Appearance	Clear liquid
Chemistry Type	Acrylic
Odor	Mild
Cure	Ultraviolet / Visible Light
Viscosity	800-900 mPas at 25°C
Flow Characteristic	Self-leveling, Newtonian fluid
Application	Prototyping
Specific Benefits	<ul style="list-style-type: none">• Good print resolution• Short exposure times• High Clarity

TYPICAL PROPERTIES OF UNCURED MATERIAL

Appearance: Clear Liquid with light blue hue
Density: 1.10
Viscosity mPa.s 800-1000
Haake Cone & Plate
RV1, C60 1 TiL, 200 s⁻¹ @ 25°C

TYPICAL PRINTER SETTINGS

The following table represents tested settings optimised for the Loctite® PR10 Printer. These settings are applicable to small test prints. Print parameters may need to be adjusted for large prints or the addition of support structures and the orientation of objects.

Print Layer	Initial Build Layer (2)	Default Build Layers
Layer Thickness (mm)	0.100	0.050
Rehab Time	2	2
Cure Time (s)	50	8.0
Retraction Height	7	7
Retraction Speed up	100	100
Time at Top	1	1
Retraction Speed Down	200	200
Light Intensity (%)	65	65

TYPICAL MATERIAL PROPERTIES OF PRINTED PARTS*

Test	Method	Results
IZOD Notched Impact	ASTM D-256	35 J/m
Tensile Strength	ASTM D638	20-40 MPa
Elongation @ Break	ASTM D638	10-20%
Tensile Modulus	ASTM D638	800 -1200MPa

The appearance of the printed part can be improved by cleaning with a fluid such as isopropanol.

*If desired by the end user, the hardness of the printed part can be improved by additional exposure to 405 nm light source.

Confidential

July 2018

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Directions for use

- 1 Wear gloves and protective glasses to prevent skin contact and for eye protection.
- 2 ****Shake well before use** and mix resin well before each print.
- 3 Do not leave resin in tray for extended periods when printer is not in use.
- 4 This material is highly photo sensitive protect from natural and artificial light sources outside of the protected printer environments.
- 5 Printer to printer variation requires adjustment of settings. Use the dosage as a guide establishing the correct printer for the specific printer that the material will be printed on.
- 6 Take care to keep printer parts clean and ensure trays and print heads are in good condition.
- 7 Calibrate printers as per user manual before printing.

Storage

Product should be stored in a dry location in unopened containers at 8-21 °C unless otherwise labelled. Storage above 28 °C is not recommended as the viscosity of the product can change at such temperatures. To prevent contamination of unused product, do not return any material to its original container.

Note

The developmental product for which the data provided herein are furnished for informational purposes only and are believed to be accurate and reliable. Nevertheless, Henkel Corporation cannot and will not assume responsibility for the results obtained by others over whose production methods we have no control. Thus, it is the user's responsibility to determine the suitability of this developmental product for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling, storage, disposal and use thereof. In light of the foregoing, **HENKEL CORPORATION SPECIFICALLY DISCLAIMS ANY**

AND ALL WARRANTIES EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE AND FREE FROM CLAIMS OF THIRD PARTY PATENT INFRINGEMENT, ARISING FROM THE SALE, POSSESSION, HANDLING, STORAGE, DISPOSAL, TRANSPORTATION OR USE OF THIS DEVELOPMENTAL PRODUCT. HENKEL CORPORATION SPECIFICALLY DISCLAIMS ANY LIABILITY FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES OF ANY KIND, INCLUDING LOST PROFITS. Neither the developmental product, nor the data or discussion herein of various processes for which, are to be interpreted as an express or implied license under any Henkel patents. Henkel Corporation recommends that any and all proposed commercial application(s) using this developmental product be evaluated for reproducibility in the exact manner and on the production equipment with which it is intended to be used before repetitive commercial production use, using this data as a guide. This developmental product may be covered by one or more United States or foreign patents or patent applications of Henkel Corporation, or under which Henkel Corporation is licensed.