

Produkt: 4701

Hersteller: H.B. FULLER

Warengruppe: KLEBSTOFF

Artikelgruppe: 1-K PU-KLEBSTOFF

Download: 29.03.2024

SWIFT® BOND 4701

Dieses Datenblatt wurde Ihnen von der Firma tewipack Uhl GmbH zur Verfügung gestellt. Die Firma tewipack Uhl GmbH übernimmt keinerlei Verantwortung für die Aktualität und die Richtigkeit der enthaltenen Informationen. Die Eigenschaften der Produkte können sich aufgrund verschiedener Einflüsse wie beispielsweise Zusammensetzung und Zustand des Substrats, Unreinheiten in oder auf dem Substrat, Temperatur und Luftfeuchtigkeit bei der Lagerung und Umgebungsbedingungen während der Anwendung ändern. Bei Verwendung dieses Produkts in Kombination mit anderem Material ist der Kunde dafür verantwortlich, durch eigene Tests zu prüfen, ob das Produkt für die geplante Kombination geeignet ist und ob diese Kombination die erwarteten Ergebnisse liefert

Swift[®] bond 4701

Type of Adhesive

Solvent-free two-component polyurethane adhesive.

Product Benefits

- solvent free
- one side application
- with Härter 414, at room temperature, the adhesive forms a firm, but still slightly flexible film
- after curing, the adhesive is highly resistant against weather conditions as well as against many chemicals, such as gasoline, oils, greases, diluted acids and alkalis
- IMO-MED certified

Typical Applications

Bonding of several substrates in different industrial applications.

Suitable substrates

Polyurethane-, PVC-, phenolic-resin- and polystyrene foams, polyester, thermo-setting plastics, laminated sheets, wood, wood materials, ceramics, concrete, fibrous cement, masonry, aluminium, steel and others.

Typical Properties

Property	Value	
	Swift [®] bond 4701	Härter 414
Base	polyurethane	isocyanate
Colour	beige	brown
Density at 20°C	approx. 1,50 g/cm ³	approx. 1,22 g/cm ³
Viscosity (Brookfield, at 20°C)	approx. 30 000 mPa.s	approx. 200 mPa.s
Mixing Ratio	100 : 20 in weight	
Density of mixture at 20°C	approx. 1,45 g/cm ³	
Mixing viscosity	approx. 7 000 mPa.s	
Hardening time	approx. 5 to 8 hours at 20°C – 22°C approx. 40 to 45 minutes at 60°C approx. 15 to 20 minutes at 100°C	
Shelf life	12 months	

**Application Instructions**

The bonding surfaces must be clean and dry. In many cases, mechanical roughening is recommended. Rigid PVC and ABS should be pre-treated with a polyurethane primer, such as Swift®prime 2200. Rubber materials need to be roughened and/or pre-treated with halogenating solution Helmitin® T/FL.

Application: by trowel

Consumption: 200 – 300 g/m², depending on surface

Pot life: approx. 40 minutes

Wet life: approx. 70 minutes

Instructions for use:

Mix the adhesive thoroughly with the hardener. For larger amount we suggest to use a mechanic mixer.

Apply the mixture on one surface to by a notched trowel. The amount depends on the surfaces to bond. Joining can be done during wet life. The parts need to be press while curing take place, even if high pressure is not required.

Higher temperature will reduce the curing time. In the case of thick and well-insulating materials, it is necessary to increase the pressing time to let the heat reach to the adhesive film. Heat curing above +60°C is not recommended for bonding of materials with a great difference in the coefficient of thermal expansion.

This adhesive cures also at low temperatures (not below +5°C). The curing time, however, will be much longer and the adhesion to metal will be reduced.

The curing process can be accelerated not only with heat, but also by adding a catalysts. Appropriate information is available upon request.

Cleaning Instructions

Please contact your local Sales Office for available cleaning solutions.

Typical Packaging

Please contact your local Sales Office for available packaging options.

Storage Conditions

In original sealed packaging protected from sun, dust, moisture and high temperatures. Clean and dry conditions above +5°C and below +35°C.

Disposal Advice

Please refer to the MSDS for disposal instructions.

Safety Advice

Please refer to the MSDS for safety advice.

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: The information, specifications, procedures and recommendations herein (together "information") are based on our experience and we believe these to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that the information will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.