

Produkt: IND403

Hersteller: HENKEL KGAA

Warengruppe: 3DP

Artikelgruppe: 3DP RESINS

Download: 18.04.2024

## LOCTITE 3D IND403 HDT80 HM BLACK

Dieses Datenblatt wurde Ihnen von der Firma tewipack Uhl GmbH zur Verfügung gestellt. Die Firma tewipack Uhl GmbH übernimmt keinerlei Verantwortung für die Aktualität und die Richtigkeit der enthaltenen Informationen. Die Eigenschaften der Produkte können sich aufgrund verschiedener Einflüsse wie beispielsweise Zusammensetzung und Zustand des Substrats, Unreinheiten in oder auf dem Substrat, Temperatur und Luftfeuchtigkeit bei der Lagerung und Umgebungsbedingungen während der Anwendung ändern. Bei Verwendung dieses Produkts in Kombination mit anderem Material ist der Kunde dafür verantwortlich, durch eigene Tests zu prüfen, ob das Produkt für die geplante Kombination geeignet ist und ob diese Kombination die erwarteten Ergebnisse liefert

**LOCTITE®**



# **LOCTITE® 3D IND403™**

HDT80 High Modulus  
Photoplastic  
Black

**LOCTITE®**

Henkel Corporation

[loctite3dp@henkel.com](mailto:loctite3dp@henkel.com)



# LOCTITE®

## IND403™

HDT80 HIGH MODULUS  
PHOTOPLASTIC  
BLACK



### LOCTITE 3D IND403™

LOCTITE 3D IND403 is a high temperature resistance material that allows the production of parts with high surface quality and outstanding dimensional accuracy.

LOCTITE 3D IND403 is ideal for tooling production for processes such as silicone casting, low pressure molding and open mold PU molding. The material can withstand mechanical stresses while maintaining dimensional stability for multiple cycles, for fast product development and rapid process iteration.



#### Benefits:

- High heat deflection temperature, HDT 80°C
- Tough with good dimensional stability
- Good surface finish



#### Ideal for:

- Tooling and molds
- Interior applications in automotive



#### Markets:



Industry



Automotive



Consumer Goods

Tensile Stress at Break (MPa)

70

Young's Modulus (MPa)

2,600

Elongation at Break (%)

10

IZOD Impact (Noched, J/m)

27

HDT at 0.455 (MPa)

80

*\*Values shown are linked to LOCTITE IND403 Black as reference, please refer to the specific mechanical properties for each of the colors shown in this document*

**Henkel**

# LOCTITE®

## IND403™

HDT80 HIGH MODULUS  
PHOTOPLASTIC  
BLACK



## PROPERTIES

Mechanical Properties	Measure	Method	Green	Post Processed
Tensile Stress at Yield	MPa	ASTM D638	40 ± 3 <sup>[1]</sup>	72 ± 2 <sup>[2]</sup>
Tensile Stress at Break	MPa	ASTM D638	32 ± 3 <sup>[1]</sup>	67 ± 3 <sup>[2]</sup>
Young's Modulus	MPa	ASTM D638	1777 ± 97 <sup>[1]</sup>	2572 ± 31 <sup>[2]</sup>
Elongation at Break	%	ASTM D638	21 ± 3 <sup>[1]</sup>	10 ± 3 <sup>[2]</sup>
Flexural Modulus	MPa	ASTM D790	1879 ± 34 <sup>[4]</sup>	2654 ± 66 <sup>[3]</sup>
Flexural Elongation at Break	%	ASTM D790	>5 <sup>[3]</sup>	>5 <sup>[3]</sup>
Flexural Stress at Break	MPa	ASTM D790	-	-
<b>Other Properties</b>				
IZOD Impact (Notched)	J/m	ASTM D256	-	27 ± 5 <sup>[7]</sup>
Shore Hardness (0s, 3s)	D	ASTM D648	81, 76 <sup>[9]</sup>	80, 78 <sup>[10]</sup>
Solid Density	g/cm <sup>3</sup>	ASTM D1475	1.17 <sup>[11]</sup>	1.20 <sup>[12]</sup>

Liquid Properties	Measure	Method	Value
Viscosity at 25°C (77°F)	cP	ASTMD7867	100 – 200 <sup>[13]</sup>
Liquid Density	g/cm <sup>3</sup>	ASTMD1475	1.08 <sup>[14]</sup>

"All specimen are printed unless otherwise noted. All specimen were conditioned in ambient lab conditions at 19-23°C / 40-60% RH for at least 24 hours." ASTM Methods: D638 Type IV, 5mm/min, D790-B, 2mm/min, D256 Notched IZOD (Machine Notched), 6 mm x 12 mm, D2240, Type "D" (0, 3 seconds), D7867, D1475

### Internal Data Sources:

[1]FOR22924, [2]FOR22926, [3]FOR20444, [4]FOR16923, [5]FOR19730, [6]FOR16920, [7]FOR16913, [8]FOR26106, [9]FOR16912, [10]FOR16911, [11]FOR16928, [12]FOR16928, [13]FOR16921, [14] FOR16910



# LOCTITE®

## IND403™

HDT80 HIGH MODULUS  
PHOTOPLASTIC  
BLACK



## PROPERTIES

Thermal Properties	Measure	Method	Green	Post Processed
HDT at 0.455 MPa	°C	ASTM D648	-	82 ± 1 [5]
HDT at 1.82 MPa	°C	ASTM D648	-	65 ± 1 [6]
Thermal Conductivity	mW/(m·K)	ASTM D5930	-	222 ± 2 [8]
Heat Capacity	J/(g·K)	ASTM D5930	-	1.46 ± 0.08 [8]

Electrical Properties	Measure	Method	Green	Post Processed
Dielectric Strength	kV/mm	ASTM D149	-	25 ± 1 [15]
Volume Resistivity	Ω·cm	ASTM D257	-	2.5 E+15 [16]
Surface Resistivity	Ω	ASTM D257	-	1.9 E+15 [16]
AC Relative Permittivity (Dielectric Constant) <sup>[17]</sup>				
at 50 Hz	none	ASTM D150	-	4.7
at 1 kHz	none	ASTM D150	-	4.5
at 1 MHz	none	ASTM D150	-	4.0
AC Loss Characteristic (Dissipation Factor) <sup>[17]</sup>				
at 50 Hz	none	ASTM D150	-	0.014
at 1 kHz	none	ASTM D150	-	0.014
at 1 MHz	none	ASTM D150	-	0.040

### Internal Data Sources:

[1]FOR22924, [2]FOR22926, [3]FOR20444, [4]FOR16923, [5]FOR19730, [6]FOR16920, [7]FOR16913, [8]FOR26106, [9]FOR16912, [10]FOR16911, [11]FOR16928, [12]FOR16928, [13]FOR16921, [14]FOR16910, [15]FOR25879, [16]FOR25878, [17]FOR25877



# LOCTITE®

## IND403™


HDT80 HIGH MODULUS  
PHOTOPLASTIC  
BLACK



## AGING AND DURABILITY EFFECTS


### EXTERIOR WEATHERING

LOCTITE 3D IND403 BK has been aged in QUV exterior weathering conditions (ASTM G-154) for 1600 hours and tested accordingly to ASTM D790<sup>[1]</sup> at standard lab conditions at 22°C.



### THERMAL AGING AT 60°C

LOCTITE 3D IND403 BK samples were kept at 60°C for 500, 1000, 2000 and 3000 hours and tested accordingly to ASTM D790<sup>[2]</sup> at standard lab conditions at 22°C.



Internal Data Sources:  
[1]FOR12709, [2]FOR14105



# LOCTITE®

## IND403™

HDT80 HIGH MODULUS  
PHOTOPLASTIC  
BLACK



## WORKFLOW

Validated workflows need to be followed to achieve properties as provided in the TDS. Examples of validated workflow steps are listed below. Users should defer to the most current workflow information for best results which can be found at <https://www.loctiteam.com/prINTER-validation-settings>

## PRINTER SETTINGS

LOCTITE 3D IND403 BK is formulated to print optimally on industrial DLP printer. Read the safety data sheet carefully to get details about health and safety instructions. Recommended print parameters:

- Shake resin bottle well before usage
- Temperature: 20°C to 45°C
- Intensity: 3 mW/cm<sup>2</sup> to 7 mW/cm<sup>2</sup>

### Exposure time for an intensity of 6 mW/cm<sup>2</sup>

Layer Thickness (µm):	100	Ec (mJ/cm <sup>2</sup> )	9.58
First layer time (s)	120	Dp (mm):	0.16
Burn in region (s):	15		
Model Layer Cure Time (s):	6.5		

## POST PROCESSING

LOCTITE 3D IND403 BK requires post processing to achieve specified properties. Prior to post curing, support structures should be removed from the printed part, and the part should then be washed. Use compressed air to remove residual solvent from the surface of the material between intervals.

Post Process Step	Agent	Method	Duration	Intervals	Additional Info
Cleaning	IPA	Ultra sonic bath	2 min	1 or 2	Allow parts to dry between intervals
Dry	n.a.	Compressed air	10 to 60 s	1 or 2	Air pressure (50psi)
Wait before post curing	n.a.	Ambient condition	60 min	1	Room temperature

## POST CURING

LOCTITE 3D IND403 BK requires post curing to achieve specified properties. It is recommended that either an LED or wide spectrum lamp be used to post cure parts.

UC Curing Unit	UV Source	Intensity	Cure time/ side	Additional Settings (Shelf, Output Energy)
Loctite CL36	405nm LED	80 mW/cm <sup>2</sup> at 405 nm	20 min	100% top & side
Loctite UVALOC 1000	Mercury Arc Bulb (broad spectrum)	30 mW/cm <sup>2</sup> at 365 nm	5 min	500 W, lowest shelf
Dymax 5000 EC Flood	Mercury Arc Bulb (broad spectrum)	150 mW/cm <sup>2</sup> at 380 nm	4 min	400W, Shelf K

**Henkel**

# LOCTITE®

## IND403™

HDT80 HIGH MODULUS  
PHOTOPLASTIC  
BLACK



## NOTE

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of **Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

### Trademark Usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.



**LOCTITE®**



**FIND OUT MORE AT**  
**LOCTITEAM.COM**

**LOCTITE®**

Henkel Corporation  
[loctite3dp@henkel.com](mailto:loctite3dp@henkel.com)



Version 2021/06/29